



Below is the Technical Data for the Precept line

DESCRIPTION	METHOD	UNIT	13" X 13"
Thickness		mm – in	7.8 mm – 5/16"
Water Absorption	EN ISO 10545-3	(%)	≤ 0.5
Abrasion Resistance	EN ISO 10545-7	(PEI)	4
Scratch Hardness		(Mohs)	7
Breaking Strength	EN ISO 10545-4	EN ISO 10545-4	≥ 330
Chemical Resistance	EN ISO 10545-13	EN ISO 10545-13	Class A – Resistant
Frost Resistance	EN ISO 10545-12	EN ISO 10545-12	Resistant
DCOF (Wet)	ANSI B101.3		≥ 0.60

DESCRIPTION	METHOD	UNIT	12" X 24"
Thickness		mm – in	9 mm – 11/32"
Water Absorption	EN ISO 10545-3	(%)	≤ 0.5
Abrasion Resistance	EN ISO 10545-7	(PEI)	4
Scratch Hardness		(Mohs)	7
Breaking Strength	EN ISO 10545-4	EN ISO 10545-4	≥ 330
Chemical Resistance	EN ISO 10545-13	EN ISO 10545-13	Class A – Resistant
Frost Resistance	EN ISO 10545-12	EN ISO 10545-12	Resistant
DCOF (Wet)	ANSI B101.3		≥ 0.60

FREDERICKSBURG SHOWROOM

2005 International Parkway
 Fredericksburg, VA 22406
 540/ 286-3000
 Fax 540/286-3126

CORPORATE HEADQUARTERS

2005 International Parkway
 Fredericksburg, VA 22406
 540/ 286-3000
 Fax 540/286-3126

FAIRFAX SHOWROOM

2803 Merrilee Drive
 Fairfax, VA 22031
 703/ 206-9111
 Fax 703/ 206-9888