

OLD FASHIONED

QUALITY CHARACTERISTICS	NORM	REQUIRED STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	$\leq 0.5\%$	$< 0.5\%$
 Breaking strenght	ISO 10545-4	$> 32 \text{ N/mm}^2$	35 N/mm^2
 Abrasion resistance	ISO 10545-7		PEI III
 Frost resistance	ISO 10545-12		frost proof
 Chemical resistance	ISO 10545-13		Conformity
 Thermal shock resistance	ISO 10545-5		Not yet tested
 Dynamic coefficient of friction	BOT 3000E	> 0.42	0.55
 Slight Variation			 Slight Variation V2



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

FOR THE BEST PRODUCT LAYING RESULTS, MATERIAL FROM AT LEAST THREE BOXES SHOULD BE MIXED



www.bfceramics.com