

Corporate Offices & Warehouse
2005 International Parkway
Fredericksburg, VA 22406

Phone
(540) 286 3000

Fax
(540) 286 3010

www.bfceramics.com
info@bfceramics.com



TECHNICAL DATA*						
ANSI A137.1: 2012 Version 1 Glazed Wall Tile, Class P4 - Non-Vitreous - 7.0% < w.a. ≤ 20.0%						
Property	Test Method	Minimum	Maximum	Obs.	Results	
CALIBRATED TILES						
	Nominal Size	ASTM C499	-2.00%	2.00%	-	OK
	Caliber Range	ASTM C499	-0.30% or -0.04 in (-1.0 mm)	0.30% or 0.04 in (1.0 mm)	1	± 0.25%
	Warpage Edge	ASTM C485	-0.30% or -0.04 in (-1.0 mm)	0.40% or 0.05 in (1.3 mm)	1	± 0.25%
	Warpage Diagonal	ASTM C485	-0.30% or -0.05 in (-1.3 mm)	0.40% or 0.07 in (1.8 mm)	1	± 0.25%
	Wedging	ASTM C502	-0.40% or -0.05 in (-1.3 mm)	0.40% or 0.05 in (1.3 mm)	1	± 0.25%
ALL TILES						
	Thickness	ASTM C499	N/A	Range: 0.031 in (0.79 mm)	3	± 5%
	Bond Strength	ASTM C482	≥ 50 psi (0.34 Mpa)	-	-	Conforms
	Water Absorption	ASTM C373	P4	P4	-	P4 (18.0% to 20.0%)
	Color Uniformity	ASTM C609	n.a.	V0 – 3 Judds	2	n.a.
	Crazing Resistance	ASTM C424	Pass	-	-	Resists
	Thermal Shock	ASTM C484	Pass	-	-	Resists
	Chemical Resistance	ASTM C650	As Reported	As Reported	-	GA, GLA
	DCOF	Section 9.6	-	-	-	-
	Stain Resistance	ASTM C1378	As Reported	As Reported	-	Class 5
	Breaking Strength	ASTM C648	Average ≥ 125 lbf (0.56 kN) Indiv. ≥ 100 lbf (0.44 kN)		-	≥ 0.50 kN
	Resistance to Freeze / Thaw Cycling	ASTM C1026	As Reported	As Reported	4	Non Resistant

n.a. Not Applicable n.p.d. No Performance Declared GL Glazed Tiles UGL Unglazed Tiles

* Whichever is less for tiles up to 24" x 24" (610 mm x 610 mm). ** Applies to tiles larger than 24" x 24" (610 mm x 610 mm).

(1) Whichever is less. (2) Glazed Tile Only. (3) Class V0 Tile Only. (4) May not apply to textured surfaces or tiles with uneven back patterns. (5) When installation subject to freeze / thaw conditions. (6) For level interior spaces expected to be walked upon when wet.

DISCLAIMER: Specifications subject to change without further notice. This information is issued as is and without any further warranty of fitness for a particular purpose, so in no event shall cinca be liable for any direct, indirect, or consequential damage whatsoever arising out of or in any way related to the use of their product.

PACKING AND WEIGHTS				
Format	Thickness	Pcs per Ctn	Box	
			Square Feet	Pounds
10"×22"	0.32 in	10	14.80	41.67
4"×12"	0.32 in	30	9.69	25.57
Bullnose	3"×10"	12	0.74	6.35



Wall Tiles



Glossy



V2

TREND

10"×22" | 4"×12"



OPULENZA



TREND

10"×22" | 4"×12"



10"×22"

WHITE



01022TWH



Wave | 01022TWWH

GREY



01022TGRY



Wave | 01022TWGRY

CHAMPAGNE



01022TC



Wave | 01022TWC

TAUPE



01022TT



Wave | 01022TWT

GREEN



01022TGRE



Wave | 01022TWGRE

BLUE




01022TBL



Wave | 01022TWBL

4"×12"



0412TWH



0412TGRY



0412TC



0412TT



0412TGRE



0412TBL

BULLNOSE
3"×10"



0310TBNWH



0310TBNGRY



0310TBNC



0310TBNT



0310TBNGRE



0310TBNBL

