



Below is the Technical Data for the Evolution line (Page 1)

DESCRIPTION	METHOD	UNIT	6" X 6"
Thickness		mm – in	8.5 mm – 11/32"
Water Absorption	EN ISO 10545-3	(%)	≤ 0.1
Abrasion Resistance	EN ISO 10545-7	(PEI)	5
Scratch Hardness		(Mohs)	7
Breaking Strength	EN ISO 10545-4	(lbf)	≥ 450
Chemical Resistance	EN ISO 10545-13	(GL)	Class A - Res.
Frost Resistance	EN ISO 10545-12		Resistant
DCOF (Wet)	ANSI B101.3		≥ 0.42

DESCRIPTION	METHOD	UNIT	12" X 12"
Thickness		mm – in	8.5 mm – 11/32"
Water Absorption	EN ISO 10545-3	(%)	≤ 0.1
Abrasion Resistance	EN ISO 10545-7	(PEI)	5
Scratch Hardness		(Mohs)	7
Breaking Strength	EN ISO 10545-4	(lbf)	≥ 450
Chemical Resistance	EN ISO 10545-13	(GL)	Class A - Res.
Frost Resistance	EN ISO 10545-12		Resistant
DCOF (Wet)	ANSI B101.3		≥ 0.42

FREDERICKSBURG SHOWROOM

2005 International Parkway
Fredericksburg, VA 22406
540/ 286-3000
Fax 540/286-3126

CORPERATE HEADQUARTERS

2005 International Parkway
Fredericksburg, VA 22406
540/ 286-3000
Fax 540/286-3126

FAIRFAX SHOWROOM

2803 Merrilee Drive
Fairfax, VA 22031
703/ 206-9111
Fax 703/ 206-9888



Below is the Technical Data for the Evolution line (Page 2)

DESCRIPTION	METHOD	UNIT	12" X 24"
Thickness		mm – in	8.5 mm – 11/32"
Water Absorption	EN ISO 10545-3	(%)	≤ 0.1
Abrasion Resistance	EN ISO 10545-7	(PEI)	5
Scratch Hardness		(Mohs)	7
Breaking Strength	EN ISO 10545-4	(lbf)	≥ 450
Chemical Resistance	EN ISO 10545-13	(GL)	Class A - Res.
Frost Resistance	EN ISO 10545-12		Resistant
DCOF (Wet)	ANSI B101.3		≥ 0.42

FREDERICKSBURG SHOWROOM

2005 International Parkway
 Fredericksburg, VA 22406
 540/ 286-3000
 Fax 540/286-3126

CORPORATE HEADQUARTERS

2005 International Parkway
 Fredericksburg, VA 22406
 540/ 286-3000
 Fax 540/286-3126

FAIRFAX SHOWROOM

2803 Merrilee Drive
 Fairfax, VA 22031
 703/ 206-9111
 Fax 703/ 206-9888