



Below is the Technical Data for the Keaton line

DESCRIPTION	METHOD	UNIT	13" X 13"
Thickness		mm - in	7.6 mm - 5/16"
Water Absorption	EN ISO 10545-3	(%)	≤ 3
Abrasion Resistance	EN ISO 10545-7	(PEI)	4
Scratch Hardness		(Mohs)	6
Breaking Strength	EN ISO 10545-4	(lbf)	≥ 250
Chemical Resistance	EN ISO 10545-13	(GL)	Class A - Resistant
Frost Resistance	EN ISO 10545-12		Resistant
DCOF (Wet)	ANSI B101.3		< 0.42

FREDERICKSBURG SHOWROOM

2005 International Parkway
 Fredericksburg, VA 22406
 540/ 286-3000
 Fax 540/286-3126

CORPORATE HEADQUARTERS

2005 International Parkway
 Fredericksburg, VA 22406
 540/ 286-3000
 Fax 540/286-3126

FAIRFAX SHOWROOM

2803 Merrilee Drive
 Fairfax, VA 22031
 703/ 206-9111
 Fax 703/ 206-9888