

FOUNDATION

QUALITY CHARACTERISTICS	NORM	REQUIRED STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	≤ 0,5 %	Conformity
 Breaking strenght	ISO 10545-4	≥ 35 N/mm ²	Conformity
 Abrasion resistance	ISO 10545-7	Powder Blue - Bronze - Sage	PEI V PEI IV
 Frost resistance	ISO 10545-12	No samples must show ruptures or noticeable surface alteration	Conformity
 Chemical resistance	ISO 10545-13		GA GLA
 Thermal shock resistance	ISO 10545-5		Conformity
 Dynamic coefficient of friction	BOT 3000E	DCOF ≥ 0,42	0.60
 Slight Variation			V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

FOR THE BEST PRODUCT LAYING RESULTS, MATERIAL FROM AT LEAST THREE BOXES SHOULD BE MIXED

www.bfceramics.com